

Standard Test Method for Rate of Water Absorption of Masonry Mortars¹

This standard is issued under the fixed designation C 1403; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a standardized laboratory procedure for determining the relative water absorption by capillary uptake (wicking) characteristics of masonry mortars. This test method is not applicable for determining the effectiveness of water repellent coatings.

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound units given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

C 109/C 109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)²

C 270 Specification for Mortar for Unit Masonry³

C 511 Specification for Moist Cabinets, Moist Rooms and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes²

C 778 Specification for Standard Sand²

3. Significance and Use

3.1 This test method provides a laboratory procedure for determining the relative water absorption properties over time of mortars used for masonry construction. Because the samples are made under laboratory conditions and do not take into account the effect of the masonry substrate or field mixing procedures, this method is not intended for field use. Data generated from this test method may be useful for determining the relative effectiveness of water repellent admixtures or the effect of other admixtures or mortar components on the water repellency of a mortar. However, use caution in interpreting the results. The relative water absorption properties of the mortar

is only one factor that affects the water penetration resistance of the masonry. The overall water penetration resistance of the masonry also depends on other factors such as extent of bond, workmanship, masonry units, etc.

4. Apparatus

4.1 *Balance*—A balance sensitive to 0.1 g.

4.2 *Immersion Tank*—A watertight container with a minimum cross section of 300 by 300 mm (12 by 12 in.) and a minimum depth of 75 mm (3 in.) and with a suitable cover to minimize evaporation. Provide specimen supports that allow a minimum of 3 mm (0.12 in.) clearance from the bottom of the container and that cover a maximum of 10 % of the specimen surface area. Provide a flat tank so that when a specimen is set on the supports the water level as specified in 6.4 shall not vary by more than 1 mm (0.04 in.) from one end of the specimen to the opposite end.

4.3 *Specimen Molds*—Metal 50-mm or 2-in. cube specimen molds with removable plastic water tight disposable liners. The plastic liners shall be rigid enough to retain their shape when free standing and filled with mortar.

4.4 *Spoon*—A metal spoon approximately 230 mm (9 in.) in length and with a bowl approximately 100 mm (4 in.) in length.

4.5 *Straightedge*—A steel straightedge not less than 150 mm (6 in.) long and approximately 1.5-3.0 mm (¹/₁₆ to ¹/₈ in.) thick.

4.6 *Tamper*—A tamper made of a nonabsorptive, nonabrasive, nonbrittle material such as a rubber compound having a Shore A durometer hardness of 80 ± 10, or seasoned oak wood rendered nonabsorptive by immersion for 15 minutes in paraffin at approximately 200°C (392°F), and having a cross section of 13 by 25 mm (0.5 by 1.0 in.) and a convenient length (127 to 152 mm (5 to 6 in.)). The tamping face of the tamper shall be flat and at right angles to the length of the tamper.

4.7 *Trowel*, having a steel blade 100 to 150 mm (4 to 6 in.) in length, with straight edges.

4.8 *Tapping Stick*—A hardwood rod, having a diameter of 16 mm (⁵/₈ in.) and a length of 150 mm (6 in.).

4.9 *Timing Device*—A suitable timing device capable of indicating elapsed time up to 24 h to the nearest 1 min.

4.10 *Calipers*—Suitable calipers with parallel jaws for measuring the dimensions of the hardened specimens to the nearest 0.5 mm.

¹ This test method is under the jurisdiction of ASTM Committee C-12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.02 on Research and Methods of Test.

Current edition approved Aug. 10, 1998. Published January 1999.

² *Annual Book of ASTM Standards*, Vol 04.01.

³ *Annual Book of ASTM Standards*, Vol 04.05.

5. Specimen Preparation

5.1 Prepare mortar according to Specification C 270 to a flow of 110 ± 5 . Record the flow. If an admixture is being added to the mortar, the time of addition shall follow the manufacturer's recommendation. Record the kind of mortar (cement/lime, mortar cement, or masonry cement), as well as, the type (O, N, S, or M) and whether the mortar is made to the proportion or property specification. Record the type and amount of each material by weight used in the mortar. In addition, record the type and amount by weight or volume of any admixture or alternative mortar material used and when it was added to the mix.

5.1.1 To test the behavior of mortar components independent of the qualities of the masonry sand use a blend of equal parts by weight of graded standard sand and standard 20 - 30 sand conforming to Specification C 778.

5.2 Prepare 50-mm or 2-in. cube specimens according to Test Method C 109/C 109M except the mortar shall be the mortar prepared in 5.1 and the molds shall be as specified in 4.3. Make a minimum of three replicate specimens from each mortar batch.

5.3 Immediately upon completion of casting, place the test specimens in a moist closet or moist room conforming to the requirements of Specification C 511. Keep all test specimens in their molds and in the moist closet or moist room for 24 ± 1 h with their upper surfaces exposed to the moist air but protected from dripping water.

5.4 At 24 ± 1 h from the time of mixing remove the specimens from the molds. Mark the side of each specimen indicating which surface is top, as cast. Cure the specimens in a moisture tight plastic bag at $24 \pm 8^\circ\text{C}$ ($75 \pm 15^\circ\text{F}$) for a total 28 days from the time of casting.

5.5 At the age of 28 days ± 12 h from the time of casting, remove the specimens from the plastic bag and dry in a ventilated oven at 110 to 115°C (230 to 240°F) for a minimum of 24 h and until the weight change is not greater than 0.2 % over a one hour period. Remove the specimens from the oven and cool in ambient conditions ($24 \pm 8^\circ\text{C}$ ($75 \pm 15^\circ\text{F}$)) for a minimum of 2 h and until the specimens reach ambient temperature. Begin testing within 48 h after reaching ambient temperature.

6. Procedure

6.1 Calculate the area of the test surface for each specimen from the length and width of the test surface. The test surface is the top face of the cube, as cast. Using calipers, measure the length of the cube test surface to the nearest 0.5 mm at three locations along its height and record as L_1 the average length in millimetres to the nearest 0.5 mm. Using calipers, measure the width of the cube test surface to the nearest 0.5 mm at three locations along its height and record as L_2 the average width in millimetres to the nearest 0.5 mm.

6.2 Record as W_0 the initial weight in grams of each individual specimen immediately prior to testing.

6.3 Place the immersion tank on a flat level surface. Place all specimens in the immersion tank(s) with their top faces, as cast, in contact with the specimen supports as illustrated in Fig. 1.

6.4 Add water to the immersion tank(s) so that the specimens are partially immersed in 3.0 ± 0.5 mm (0.12 ± 0.02 in.) of water. Cover the immersion tank(s) to minimize evaporation.

6.5 At 0.25, 1, 4, and 24 h, measure the weight in grams of each specimen and record as W_T where T is the measurement




FIG. 1 Specimen Configuration During Testing

time in hours. Wipe off surface water from each specimen with a damp cloth prior to each weighing. Complete the wipe within 10 s of removal from contact with the water and complete weighing within 1 min.

6.6 After each weighing, replace the specimens into the immersion tank(s) and add water as necessary to maintain the immersion depth specified in 6.4. Re-cover the immersion tank(s).

7. Calculation

7.1 Calculate and record as A_T the water absorption in grams/100 cm², at each time period, T , for each specimen, as follows:

$$A_T = (W_T - W_0) \times 10\,000 / (L_1 \times L_2) \quad (1)$$

where:

W_T = the weight of the specimen at time T in grams,

W_0 = the initial weight of the specimen in grams,

L_1 = the average length of the test surface of the mortar specimen cube in mm to the nearest 0.5 mm, and

L_2 = the average width of the test surface of the mortar specimen cube in mm to the nearest 0.5 mm.

7.2 Calculate and record as, A_T (avg), the average A_T for each set of three or more replicate specimens at each time interval.

8. Report

8.1 Report the mortar mixture, as follows:

8.1.1 The kind of mortar (cement/lime, mortar cement, or masonry cement),

8.1.2 The type (O, N, S or M) used,

8.1.3 Whether the mortar was made to the proportion or property specification,

8.1.4 The type and amount of each material by weight used in the mortar,

8.1.5 The type and amount by weight or volume of any admixture or alternative mortar material used in the mortar and when it was added to the mix, and

8.1.6 The actual flow of the mortar batch(es).

8.2 Report the water absorption test results, as follows:

8.2.1 For each specimen, report:

8.2.1.1 L_1 , the average length of the test surface of the mortar specimen cube in mm to the nearest 0.5 mm,

8.2.1.2 L_2 , the average width of the test surface of the mortar specimen cube in mm to the nearest 0.5 mm,

8.2.1.3 W_0 , the initial weight of the specimen in g,

8.2.1.4 $W_{0.25}$, the weight of the specimen at 0.25 h in g,

8.2.1.5 W_1 , the weight of the specimen at 1 h in g,

8.2.1.6 W_4 , the weight of the specimen at 4 h in g,

8.2.1.7 W_{24} , the weight of the specimen at 24 h in g,

8.2.1.8 $A_{0.25}$, the water absorption of the specimen at 0.25 h in g/100 cm²,

8.2.1.9 A_1 , the water absorption of the specimen at 1 h in g/100 cm²,

8.2.1.10 A_4 , the water absorption of the specimen at 4 h in g/100 cm², and

8.2.1.11 A_{24} , the water absorption of the specimen at 24 h in g/100 cm².

8.2.2 For each set of three or more replicates, report:

8.2.2.1 $A_{0.25}(\text{avg})$, the average water absorption at 0.25 h in g/100 cm²,

8.2.2.2 $A_1(\text{avg})$, the average water absorption at 1 h in g/100 cm²,

8.2.2.3 $A_4(\text{avg})$, the average water absorption at 4 h in g/100 cm², and

8.2.2.4 $A_{24}(\text{avg})$, the average water absorption at 24 h in g/100 cm².

9. Precision and Bias

9.1 A precision and bias statement is not available for this test method.

10. Keywords

10.1 absorption; absorption rate; masonry mortar; water repellent

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.