



## Standard Test Method for Change in Height at Early Ages of Cylindrical Specimens from Cementitious Mixtures<sup>1</sup>

This standard is issued under the fixed designation C 827; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

---

<sup>ε1</sup> NOTE—Section 13, Keywords was added editorially in July 1997.

---

### 1. Scope

1.1 This test method covers the determination of change in height of cylindrical specimens from the time of casting until the mixture is hard. If desired, this test method can be adapted to studies of changes in height involving different time schedules or other environmental treatment from the standard procedures prescribed by this test method.

1.2 This test method covers height change measurements at early ages for cementitious mixtures of paste, grout, mortar, and concrete.

1.3 Use of this test method is suggested for determination of changes in height that occur from the time of placement until the specimen is fully hard. These include shrinkage or expansion due to hydration, settlement, evaporation, and other physical and chemical effects.

1.4 The phrase “early age change in height” as used herein, is defined as the measured increase or decrease in height of a laterally confined cylindrical test specimen from the time of casting to when the mixture becomes hard. The user may want to define this age as the time when a companion specimen of the same batch has reached the time of final setting by Test Method C 191 (paste), C 953 (mortar or grout), C 403 (concrete), or establish a predetermined age in minutes from the time the specimen is cast as the defined age to record the final measurement. Changes in height are measured and expressed as a positive or negative change in the height of a test specimen that is restrained from lateral movement.

1.5 The values stated in SI units are to be regarded as the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

---

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C-9 on Concrete and Concrete Aggregates, and is the direct responsibility of Subcommittee C09.68 on Volume Change.

Current edition approved April 15, 1995. Published July 1995. Originally published as C 827 – 75 T. Last previous edition C 827 – 95.

- C 109/C 109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or 50-mm Cube Specimens)<sup>2</sup>
- C 143 Test Method for Slump of Hydraulic Cement Concrete<sup>3</sup>
- C 191 Test Method for Time of Setting of Hydraulic Cement by Vicat Needle<sup>2</sup>
- C 192 Practice for Making and Curing Concrete Test Specimens in the Laboratory<sup>3</sup>
- C 305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency<sup>2</sup>
- C 403 Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance<sup>3</sup>
- C 670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials<sup>3</sup>
- C 807 Test Method for Time of Setting of Hydraulic Cement Mortar by Modified Vicat Needle<sup>2</sup>
- C 939 Test Method for Flow of Grout for Preplaced-Aggregate Concrete (Flow Cone Method)<sup>3</sup>
- C 953 Test Method for Time of Setting of Grouts for Preplaced-Aggregate Concrete in the Laboratory<sup>3</sup>

### 3. Significance and Use

3.1 This test method affords a means for comparing the relative shrinkage or expansion of cementitious mixtures. It is particularly applicable to grouting, patching, and form-filling operations where the objective is to completely fill a cavity or other defined space with a freshly mixed cementitious mixture that will continue to fill the same space at time of hardening. It would be appropriate to use this test method as a basis for prescribing mixtures having restricted or specified volume change before the mixture becomes hard.

3.2 This test method can be used for research purposes to provide information on volume changes taking place in cementitious mixtures between the time just after mixing and the time of hardening. However, the specimen used in this test method is not completely unrestrained so that the measurements are primarily useful for comparative purposes rather than as absolute values. Further, the degree of restraint to which the specimen is subjected varies with the viscosity and degree of hardening of the mixture.

---

<sup>2</sup> Annual Book of ASTM Standards, Vol 04.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 04.02.




FIG. 1 Apparatus for Early Change in Height

#### 4. Apparatus (see Fig. 1)

4.1 *Projected Light Source*—The projected light source shall consist of a lamp and a condensing lens and be of sufficient intensity to adequately project a light beam on a wall about 5 m (or 15 ft) from the light source. Heat from the light source should not be directed toward the test specimen.

4.2 *Indicator Ball*—The indicator ball shall be a spherical ball of nonabsorptive material with a density that is  $55 \pm 5\%$  of the density of the cementitious mixture being tested (Note 1). The diameter shall not be more than 16 mm (or  $\frac{5}{8}$  in.) nor less than 6 mm (or  $\frac{1}{4}$  in.). The indicator ball shall be composed of materials that have no reaction with the cementitious mixture during the test period.<sup>4</sup>

NOTE 1—A density of approximately 1.2 mg/m<sup>3</sup> has been found appropriate for most uses of this test method.

4.3 *Magnifying Lens System*—The magnifying lens system shall cause the image of the indicator ball produced by the projected light source to be cast on the indicating chart about 5 m (or 15 ft) away at a magnification of 90–110 $\times$ . The system shall be able to be mounted so as not to touch the test specimen when a test is in progress (see Note 2). A separate magnifying lens system will be required for each specimen tested simultaneously.

NOTE 2—One magnifying lens system that has been found acceptable consists of two lenses: a projection and a relay lens enclosed in a sealed tube. In this system, the relay lens is located nearest the test specimen and has a focal length of 50.8 mm (or 2 in.) and is located approximately 114.3 mm (or 4½ in.) from the indicator ball. The projection lens has a focal length of 41.4 mm (or 1½ in.), and relative aperture of  $f/1.6$  and is 133.1 mm (or 5¼ in.) from the relay lens.

4.4 *Indicating Charts*—These charts shall be composed of stiff material approximately 600 mm (or 24 in.) high by 250 mm (or 10 in.) wide. The chart shall have a white surface with a vertical black line 2 mm (or  $\frac{1}{16}$  in.) wide, centered and running the complete length of the chart, and a horizontal black line 1 mm (or  $\frac{1}{32}$  in.) in width midway on the chart, identified as the zero (0) or starting line. The vertical line shall have 2 mm (or  $\frac{1}{16}$  in.) horizontal graduations above and below the zero line on its entire length. A means for attaching this chart vertically and firmly to a distant wall shall be provided.

4.5 *Molds*—The molds for the test specimens shall be

rigid, watertight, have a smooth interior surface, and may be made of steel, cast iron, or other nonabsorbent material nonreactive with the cementitious mixture being tested. The molds shall be of a cylindrical shape with internal height twice the internal diameter. Three sizes of molds are used in this method with heights of 100, 150, 300 mm (or 4, 6, 12 in.).

4.6 *Rods*—Two straight, steel tamping rods: one 10 mm (or  $\frac{3}{8}$  in.) in diameter and approximately 300 mm (or ½ in.) in length and the other 16 mm (or  $\frac{5}{8}$  in.) in diameter and approximately 600 mm (or 24 in.) in length shall be used, for grout and mortar, or concrete respectively.

#### 5. Test Specimens

5.1 Unless otherwise specified, two test specimens shall be prepared from each batch and tested simultaneously using duplicate test apparatus. For cement pastes, grouts, and mortars where all the aggregate will pass through a 4.75-mm (No. 4) sieve, the cylinder mold height shall be 100 mm (or 4 in.). For cementitious mixtures containing aggregate that will not all pass through a 4.75-mm (No. 4) sieve, but which will all pass the 12.5-mm (½-in.) sieve, the cylinder mold height shall be 150 mm (or 6 in.). For concrete mixtures having particles retained on the 12.5 mm (½-in.) sieve or larger, the cylinder mold height shall be 300 mm (or 12 in.).

#### 6. Calibration

6.1 *General*—Provision should be made for minimizing any sources of light not required for the tests. Locate the test equipment and specimens on a surface substantially free of vibration during the test. If desired, use a single projected light source for both test specimens with duplicate magnifying lens systems and indicating charts.

6.2 *Apparatus Calibration*—Calibrate the entire apparatus prior to the start of each test. Darken the laboratory, illuminate the projected light source, and locate the dummy test specimens (preferably hardened test specimens) in the light beam before each of the magnifying lens systems. Adjust the location of each test specimen until a sharp, clear image of the indicator ball is produced on the indicating chart. Then reposition the indicating chart so that the indicating ball image falls on the zero line. Place a steel rod of known diameter (see Note 3) horizontally on top of each indicator ball and record the height of the image it produces on its respective indicating chart. The ratio of the image height to the actual rod diameter is the magnification of the

<sup>4</sup> A 11-mm ( $\frac{7}{16}$ -in.) nylon plastic indicator ball has been found acceptable for most tests and is available from U.S. Plastics Corp., 1390 Neubrecht Rd., Lima, OH 45801.

lens system. The magnification can be changed by moving the projected light source, test specimen, and magnifying lens system toward or away from the indicating chart. Once proper magnification (90 to 110×) is obtained, remove the dummy test specimens and do not change the relative locations of all test apparatus during the test.

NOTE 3—The shank of a 2 mm (or 1/16 in.) twist drill bit has been found satisfactory for most tests.

## 7. Preparation of Mixtures

7.1 *General*—Bring all materials to a temperature of  $21 \pm 3^\circ\text{C}$  (or  $70 \pm 5^\circ\text{F}$ ) before mixing. In the case of field-mixed materials, record the temperature of the mixture just prior to placing in a test cylinder as well as the ambient temperature of the test area immediately around the specimen. Proportion all materials by mass in accordance with the specifications for the cementitious mixtures to be tested.

### 7.2 Mortars, Pastes, and Grouts:

7.2.1 Either hand mix or use a suitable mechanical mixer (see Note 4) for a mixing time of 4 min, unless otherwise recommended by the manufacturer. Place all the water in the mixing bowl prior to introduction of the other materials for the batch. For mortar materials that are not premixed, the sequence of mixing shall be in accordance with Practice C 305.

NOTE 4—The mechanical mixer described in Practice C 305 is a suitable mixer. However, the clearances between paddle and bowl specified in this method are suitable only for mortars made with fine aggregates that are finer than the 850- $\mu\text{m}$  (No. 20) sieve. Mortars made with aggregates containing particles coarser than the 850- $\mu\text{m}$  (No. 20) sieve may require special clearances or a different type of paddle to permit the mixer to operate freely and to avoid damage to the paddle and bowl.

7.2.2 Determine the consistency of the mixtures by the flow test in accordance with the applicable provisions of Test Method C 109, if when this procedure is used, the flow after 5 drops of the flow table in 3 s is 145 or less. A plastic mixture should have a flow of 100 to 125, and a flowable mixture should have a flow above 125 when tested by the above modification of Test Method C 109 but not less than 30 s when tested using the flow-cone procedure of Test Method C 939. A fluid mixture should have a time of efflux of 10 to 30 s when tested by the flow-cone procedure. The water required to produce the specified consistency shall be determined by the testing of trial batches. Fresh materials shall be used to make each trial. If not specified or recommended otherwise, use sufficient mixing water to produce a flow of  $135 \pm 5$ . For premixed mortars or grouts, use the amount of water suggested by the manufacturer for the intended application. The consistency should be determined and the values recorded for all tests.

7.3 *Concrete*—Mix concrete either manually or in a suitable laboratory mixer in accordance with the applicable provisions of Practice C 192. Determine the consistency of the concrete by the slump test in accordance with the applicable portions of Test Method C 143, and unless otherwise specified, use sufficient mixing water to produce a slump of  $90 \pm 15$  mm (or  $3\frac{1}{2} \pm \frac{1}{2}$  in.).

## 8. Molding Specimens

8.1 Mold all test specimens and start the test 1 min after completion of mixing.

8.2 Fabricate 100 mm and 150 mm (or 4 in. and 6 in.) specimens by filling the mold in a continuous pouring operation for pourable mixtures or in two layers with consolidation of each layer by tapping the outside of the mold ten times with a 10-mm (or 3/8-in.) diameter rod in the case of mixtures that are not pourable. Fabricate 300-mm (or 12 in.) specimens in accordance with Practice C 192.

8.3 Screed off the surface of the test specimen to the top of the mold. In cases where extreme shrinkage or expansion of material is anticipated, adjust the height of the test material to  $\pm 6$  mm (or 1/4 in.) with respect to the mold height.

## 9. Procedure

9.1 Place an indicator ball in the center of the surface of each specimen. Tap the indicator ball lightly so that approximately one half of its diameter penetrates the test specimen mixture. Remove pieces of large aggregate directly under the indicator balls, and repeat the procedure. Then tap the outer side of the molds lightly three times so that the indicator balls can adjust to their own natural displacement level in the mixture. Position each specimen between the projected light source and the magnifying lens system. Adjust the position of the test specimens horizontally until the images of the indicator balls on the indicating charts are sharp and clear. Reposition the indicating charts so that the indicating ball images fall on the zero lines. This time shall be noted as the start of the test and shall meet the time requirement stated in the section on molding specimens. Unless otherwise specified, conduct tests with test specimens that are free to evaporate to the atmosphere. Record ambient air temperature and humidity. If a moist storage condition is specified, place a few drops of medium-weight motor oil on the test specimen surface to allow an oil film to cover the exposed surface of the test specimen. During the test, carefully place additional drops of oil on the test specimen surface by an eyedropper or other suitable means, taking care not to touch the indicator ball.

9.2 *Test Measurements*—Once the test specimens are placed in position, do not jar, touch, or move the test apparatus until the completion of the test. Record movements of the indicator balls as projected on the indicating charts at 5-min intervals during the first 90 min, at 10-min intervals for the next 1 h, and at 20-min intervals thereafter until the mixture has hardened (Note 5). Clearly identify all readings from the charts as positive (+) for increase in height, and negative (−) for decrease in height, read to the nearest 0.1-in. (or 2-mm) graduation vertically, and record the time to the nearest 1 min.

NOTE 5—Time of hardening may be taken as the time of final setting as determined by Test Methods C 191 for cement pastes, C 807 for mortars and nonfluid grouts, C 953 for fluid grouts, and C 403 for concrete mixtures. Measurements may be continued after hardening, if desired.

## 10. Calculation

10.1 *Change in Height of Specimen*—Calculate the changes in height of the test specimens as follows:

$$\Delta H = (I/MH) \times 100$$

where:

$\Delta H$  = change in height, expressed in %: positive (+) for increase, negative (−) for decrease,

- $I$  = indicating chart reading, in. (or mm): positive (+) for increase, negative (–) for decrease in height,  
 $H$  = initial height of test specimen, in. (or mm), and  
 $M$  = magnification of lens system.

## 11. Report

11.1 Plot the changes in height as points on a graph, with increase (+) above the zero line and decrease (–) below the zero line. Report all change in height and time readings from the start of the test to conclusion, as percent versus time. Show the average of the data as a smooth curve. Calculate the maximum change in height using the largest indicating chart reading obtained during the test period and report as increase or decrease. In the event that both increase and decrease result, report the maximum change in height.

11.2 The report shall also include the following:

11.2.1 Number and size of specimens tested and the date,

11.2.2 Source and identification of all materials used in the mixtures,

11.2.3 Flow, slump, or qualitative consistency of the mixture,

11.2.4 Magnification,

11.2.5 Temperature of the test mixture, ambient temperature at time of molding specimens, and ambient temperature and relative humidity throughout the test period if the test specimens are allowed to dry by exposure to the atmosphere,

11.2.6 Time interval from addition of the batch to the

mixing water in the mixer to the time of start of test,

11.2.7 Magnitude and time of occurrence of maximum decrease, maximum increase in height, change in height at time of hardening of the mixture, and change in height at the conclusion of the test, and

11.2.8 Any other information that may be pertinent.

## 12. Precision and Bias

12.1 *Precision*—The single-operator standard deviation for sand/cement mixtures has been found to be 0.12 % (Note 6) change in height. Therefore, results of two properly conducted tests by the same operator on the same material should not differ by more than 0.34 % change in height.

12.2 The single-operator standard deviation for cement paste has been found to be 0.43 % (Note 6) change in height. Therefore, results of two properly conducted tests by the same operator on the same material should not differ by more than 1.22 % change in height.

NOTE 6—These numbers represent, respectively, the (1s) and (d2s) limits as described in Practice C 670. Data were from tests of specimens 4 in. in height.

12.3 *Bias*—This test method has no bias because the value of the change in height can only be defined in terms of a test method.

## 13. Keywords

13.1 change in height; cementitious mixtures; concrete; expansion; grout height change; mortar; paste; shrinkage

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*