



Standard Specification for Foaming Agents Used in Making Preformed Foam for Cellular Concrete¹

This standard is issued under the fixed designation C 869; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers foaming agents specifically formulated for making preformed foam for use in the production of cellular concrete.

1.2 The function of this specification is to provide the means for evaluating the performance of a specific foaming agent. This is accomplished by using the foaming agent in making a standard cellular concrete test batch (see Method C 796) from which test specimens are cast. Then, significant properties of the concrete are determined by tests and compared with the requirements of Section 3.

1.3 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 *ASTM Standards:*

C 796 Test Method for Foaming Agents for Use in Producing Cellular Concrete Using Preformed Foam²

3. Performance Requirements

3.1 The test batch shall conform to the requirements prescribed in Table 1.

4. Test Methods

4.1 The foaming agent being tested shall be used in making the test specimens required.

4.2 For each of the properties listed in Table 1, the test procedure, the number and type of test specimens, and the method of molding, curing, and testing shall be as described in Method C 796.

5. Keywords

5.1 cellular concrete; foaming agents

¹ This specification is under the jurisdiction of ASTM Committee C-9 on Concrete and Concrete Aggregates, and is the direct responsibility of Subcommittee C09.23 on Chemical Admixtures.

Current edition approved Dec. 23, 1991. Published February 1992. Originally published as C 869 – 77. Last previous edition C 869 – 80 (1986).

² *Annual Book of ASTM Standards*, Vol 04.02.

TABLE 1 Physical Requirements

Property	Requirement
<i>Density</i> —The density shall satisfy either of the following:	
Density after pumping (see Method C 796)	40 ± 3 lb/ft ³ (641 ± 48 kg/m ³)
Oven dry density ^A (see Method C 796)	
For Type I cement	30.4 ± 2.5 lb/ft ³ (487 ± 40 kg/m ³)
For Type III cement	29.3 ± 2.5 lb/ft ³ (469 ± 40 kg/m ³)
<i>Compressive Strength</i> (see Method C 796), min	200 psi (1.4 MPa)
<i>Tensile Splitting Strength</i> (see Method C 796), min	25 psi (0.17 MPa)
<i>Water Absorption</i> (see Method C 796), max	25 % by volume
<i>Loss of Air During Pumping</i> (see Method C 796), max ^B	4.5 % by volume

^A For this comparison, the calculated oven-dry density of the test batch may be determined by assuming that the water of hydration is 20 % of the weight of the cement. Then the oven-dry density = $\frac{W_c + (0.2 W_c)}{V_{\text{batch}}}$, where W_c = weight of cement; and V_{batch} = volume of batch.

For example: using the test batch specified in Method C 796, for Type I cement ($W_c = 100$ lb; $W_{TW}/W_c = 0.58$, where W_{TW} = total weight of water), the total weight of materials is $100 + 0.58 \times 100 = 158$ lb (71.67 kg). For a wet density, after pumping, of 40 lb/ft³ (641 kg/m³), the batch volume is $158/40 = 3.95$ ft³ (0.11185 m³). The calculated oven dry density is then $(100 + 0.2 \times 100)/3.95 = 30.4$ lb/ft³ or $(45.36 + 0.2 \times 45.36)/0.11185 = 487$ kg/m³. Finally, the oven-dry density as determined by Method C 796 shall be 30.4 ± 2.5 lb/ft³ (487 ± 40 kg/m³).

^B The loss of air during pumping includes air that is accidentally entrapped during mixing of the concrete.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 1916 Race St., Philadelphia, PA 19103.